





BHIMAFIX DYES		Product Name C.I. No.	Processes		
			Exhaust Dyeing	Semicontinuous Dyeing	Continuous Dyeing
1%	4%				
		BHIMAZOL BLACK B - 200% *Black 5	S	S	NS
		BHIMAFIX BLACK Mix *Mix	S	S	S
		BHIMAZOL T. BLUE G - 266% *Blue 21	S	S	NS

Dischargeability	Solubility g/l		Light Fastness				Washing		Water		Perspiration E04				Rubbing	
	Water - 30°C	Salt (90 g/l) - 50°C	AATCC 16E 1/1	AATCC 16E 1/3	ISO BO2 1/1	ISO BO2 1/3	CO3		E01		Acidic		Alkaline		X12	
							Change in colour	Stain (cotton)	Change in colour	Stain (cotton)	Change in colour	Stain (cotton)	Change in colour	Stain (cotton)	Dry Rubbing	Wet Rubbing
D	200	180	4-5	4	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4
D	200	200	4	4	4	4-5	4	4	4	4-5	5	4	4-5	4	4	4
F	150	150	4-5	4	6	5	4	4-5	4-5	4	4-5	4	4	4	4-5	4-5